

Typical Electrical Resistivity: Linard HD 60 vs. Linatex

Test Method: BS 903: Part C1 (1991) & Part C2 (1982)

Volatage applied: 500 V

	Linatex	<b>Linard HD 60</b>
Surface Resistivity Ohms	$1.32 \times 10^{13}$	<b><math>2.42 \times 10^7</math></b>
Volume Resistivity Ohm-cm	$3.03 \times 10^{14}$	<b><math>1.02 \times 10^7</math></b>