

Rubber Sheeting

Electrical resistivity

E550 EPDM

01/2018

Atex DIRECTIVE 2014/34/EU does not apply to rubber sheeting. However, below a value of $10^9 \Omega$, surface resistivity, can be considered low enough to avoid dangerous electrostatic discharge risk.

This risk will depend on final product, application and installation.

Test:	Several
Standard	ISO 14309
Surface resistivity	$4 \times 10^5 \Omega$
Volume resistivity	$1,3 \times 10^4 \Omega \cdot m$

