

Broad ribbed



REACH



MECHANICAL	Standard	Value	
Rubber compound		SBR/NR	
Density		1.50 +/-0.05	g/cm3
Hardness	DIN 53519	65 ⁰ +/-5	Shore A
Tensile strength	DIN 53504	4	MPa
Elongation at break	DIN 53504	180	%
Tear resistance			N/mm
Compression set			%

TEMPERATURE	
Working temperature	-30°C / +60°C

AGEING	
Δ Hardness	%
Δ Tensile strength	N/mm
Δ Elongation at break	%

OIL RESISTANCE	
Oil IRM 901, Δ volume	%
Oil IRM 903, Δ volume	%

CHEMICAL RESISTANCE	
Diluted acids and bases	Medium
Concentrated acids and basis	Not suitable
Ozone	Medium
Oils and hydrocarbons	Not Suitable

DIMENSIONS						
SKU	Thickness (mm)	Width (mm)	Length (m)	Inserts	Colour	
30120100	5	1000	10	0	black	
30120120	5	1200	10	0	black	
30120145	5	1400	10	0	black	
30120101	6	1000	10	0	black	
30120121	6	1200	10	0	black	
30120122	8	1200	10	0	black	
30120140	6	1400	10	0	black	