

Rubber Sheeting

Electrical resistivity

CF03 CR

16/11/2020

Atex DIRECTIVE 2014/34/EU does not apply to rubber sheeting. However, below a value of $10^9 \Omega$, surface resistivity, can be considered low enough to avoid dangerous electrostatic discharge risk.

This risk will depend on final product, application and installation.

Test report number	Several
Standard	ISO 14309
<i>Surface resistivity</i>	$1,0 \times 10^9 \Omega$
<i>Volume resistivity</i>	$1,0 \times 10^7 \Omega \cdot m$

