

**Advanced Materials****ARALDITE® 2014-3 (ARALDITE® AW 139-2 / Hardener HW 5323-1)****Structural Adhesives****PROVISIONAL TECHNICAL DATA SHEET****Two-component epoxy paste adhesive****Key properties**

- Dark grey paste
- High temperature and chemical resistance
- Very resistant to water and to a wide variety of chemicals
- Gap filling, non-sagging up to 5mm thickness

**Description**

ARALDITE® 2014-3 (bulk-pack reference: ARALDITE® AW 139-2 / Hardener HW 5323-1) is a two-component, room-temperature curing, sag-resistant paste adhesive with high strength and good environmental and chemical resistance. It can be used for bonding metals, electronic components, composite materials and many other applications where higher temperatures or aggressive environmental conditions are encountered in service.

**Product data**

Property	RESIN ARALDITE® 2014-3 A (AW 139-2)	HARDENER ARALDITE® 2014-3 B (HW 5323-1)	MIXED ADHESIVE
Appearance (visual)	beige paste	dark grey paste	dark grey paste
Specific gravity	ca. 1.6	ca. 1.5	ca. 1.6
Viscosity at 25°C	50 – 80 Pa.s	thixotropic	thixotropic
Working time (10g) 23°C	-	-	ca. 120 min

*Data in this document shows 'typical' values and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.*

**Processing****Pretreatment**

The strength and durability of a bonded joint are dependent on proper pretreatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as methoxy propanol, acetone or other proprietary degreasing agents to remove all traces of oil, grease and dirt. Low grade alcohol, gasoline (petrol) or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching ("pickling") the degreased surfaces. Abrading should be followed by a second degreasing treatment prior to bonding.

Mix ratio	Parts by weight	Parts by volume
ARALDITE® 2014-3 A (AW 139-2)	100	100
ARALDITE® 2014-3 B (HW 5323-1)	50	50

**Application of adhesive**

The resin/hardener mix may be applied manually or using automated application to pretreated surfaces ready for bonding. Huntsman's technical support group can advise further on surface pre-treatments as well as suitable application methods and dispensing equipment.

An adhesive bond thickness of 0.1 to 0.30 mm will typically impart the greatest lap shear strength to a joint. Proper adhesive joint design and surface preparation is critical to produce a durable bond. The bonded components should be assembled and held in a fixed position as soon as the adhesive has been applied, at least until the handling strength is reached (handling strength considered as 1MPa lap shear strength – see table below).

For more information regarding surface preparation and pretreatment, adhesive joint design, dispensing systems and adhesive properties, visit [www.aralditeadhesives.com](http://www.aralditeadhesives.com) and download the Technical Guide for ARALDITE® Adhesives.

**Equipment maintenance**

Tools should be cleaned using a suitable solvent, such as methoxy propanol or acetone, before adhesive residues have had time to cure. Removal of cured residues with solvents is not possible, and mechanical abrasion must be used. If solvents are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

**Typical times to minimum shear strength**

Temperature	°C	10	15	23	40	60	100
Cure time to reach	hours	13	9	4	-	-	-
LSS > 1MPa	minutes	-	-	-	70	13	1
Cure time to reach	hours	21	12	6	-	-	-
LSS > 10MPa	minutes	-	-	-	95	21	2


LSS = Lap shear strength.

**Typical cured properties**

The data shown below is provided solely as technical information and does not constitute a product specification. Unless otherwise stated, the figures given below were determined by testing standard specimens made by lap-jointing 100 x 25 x 1.6 mm strips of sandblasted aluminium alloy. The bond area was 12.5 x 25 mm, with bonded specimens cured under light clamping pressure. Lap shear testing was carried out at 23°C at 10mm/min unless otherwise stated.

### Average lap shear strengths of typical metal-to-metal joints (ISO 4587; typical average values)


Cured 16 hours at 40°C and tested at 23°C. Pretreatment: sandblast + degrease



\* galvanised steel: degrease only

### Average lap shear strengths of typical plastic-to-plastic joints (ISO 4587; typical average values)


Cured 16 hours at 40°C and tested at 23°C. Pretreatment: light abrasion + degrease.



\* substrate failure

### Lap shear strength versus temperature (ISO 4587; typical average values)

Aluminium 5754, pretreatment: sandblast + degrease. Cure a: 16 hrs at 40°C, cure b: 24 hrs at RT + 1hr 80°C



**DMA (Dynamic Mechanical Analysis ISO 6721; typical average values)****Cure a: 16 hours 40°C**

Tg midpoint	69°C
Shear modulus -40°C	2199 MPa
Shear Modulus 23°C	1667 MPa
Shear Modulus 50°C	1241 MPa
Shear Modulus 75°C	31 MPa
Shear Modulus 100°C	22 MPa
Shear Modulus 125°C	23 MPa

**Cure b: 24 hours at RT + 1 hour 80°C**

Tg midpoint	96°C
Shear modulus -40°C	2097 MPa
Shear Modulus 23°C	1544 MPa
Shear Modulus 50°C	917 MPa
Shear Modulus 75°C	282 MPa
Shear Modulus 100°C	41 MPa
Shear Modulus 125°C	22 MPa

**Tensile Properties (ISO 527; typical average values) Cure 16 hours at 40°C, tested at 23°C**

Tensile modulus	3700 MPa
Tensile strength	45 MPa
Elongation at break	1.6 %

**Compressive Properties (ISO 604; typical average values) Cure 16 hours at 40°C, tested at 23°C**

Compressive modulus	3285 MPa
Maximum compressive strength	104 MPa
Strength at break	88 MPa

**Hardness (ISO 868; typical average values) Cure 16 hours at 40°C, tested at 23°C**


Shore D hardness	81
------------------	----

**Electrical Properties (typical average values) Cure 16 hours at 40°C, tested at 23°C**

Property	Test values	Test method
Dielectric strength (kV/mm)	20.9	IEC 60243-1:2013, IEC 60455-2:2015
Surface resistivity (Ohm)	$3.7 \times 10^{14}$	IEC 62631-3-1 / IEC 60093
Volume resistivity (Ohm.cm)	$3.5 \times 10^{15}$	IEC 62631-3-1 / IEC 60093
Dielectric constant at 60Hz	4.4	IEC 62631-2-1 / IEC 60093
Loss tangent, % at 60Hz	1.6	IEC 62631-2-1 / IEC 60093

### Lap shear strength versus immersion in various media (ISO 4587; typical average values)


Aluminium 5754, cured 16 hours at 40°C and tested at 23°C. Pretreatment: sandblast + degrease



### Lap shear strength versus tropical weathering (DIN 50015; typical average values)

Aluminium 5754, cured 16 hours at 40°C and tested at 23°C. Pretreatment: sandblast + degrease


Tropical weathering: 40°C, 92% relative humidity



### Lap shear strength versus heat ageing at 70°C (ISO 4587; typical average values)


Aluminium 5754, cured 16 hours at 40°C and tested at 23°C. Pretreatment: sandblast + degrease

Heat aging at 70°C



### Lap shear strength versus cataplasma ageing (ISO 9142 E2; typical average values)

Aluminium 5754, cured 16 hours at 40°C and tested at 23°C. Pretreatment: sandblast + degrease



---

**Storage**

ARALDITE® 2014-3 (AW 139-2 / HW 5323-1) should be stored at room temperature in the original sealed containers, kept in a dry place protected from extremes of temperature and strong sunlight. The expiry date is indicated on the individual container labels.

---

**Handling precautions****Caution**

Our products are generally safe to handle when standard chemical handling practices are followed. Uncured materials must **never** come into contact with food or food utensils. Avoid skin contact, as individuals with sensitive skin may experience irritation. Wear **impervious rubber or plastic gloves** and **eye protection** during handling. At the end of each work period, wash skin thoroughly with **soap and warm water**—do **not** use solvents. Dry with **disposable paper towels**, not cloth. Ensure **adequate ventilation** in the working area. For full details, refer to the **Safety Data Sheet (SDS)** for the specific product.

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, **nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.**

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2025 Huntsman Corporation or an affiliate thereof. All rights reserved

**Huntsman Advanced  
Materials (Switzerland) GmbH**  
Klybeckstrasse 200  
CH - 4057 Basel  
Switzerland

Tel: +41 (0)61 299 11 11

[www.huntsman.com](http://www.huntsman.com)