


Vera – oil resistant

NR/SBR

Typ 8

Product features

- NR/SBR, terracotta
- Resistant to not aromatic oil
- Open base



Product specifications

• Colour	Terracotta
• S.G. grs/cm ³	1.50
• Hardness °Shore A ± 5° (DIN 53519)	55
• Tensile strength MPa (DIN 53504)	4
• Elongation % (DIN 53504)	200
• Abrasion Resistance mm ³ (DIN 53516)	-
• Compression set % (DIN 53517)	-
• Tear Strength kN/m (DIN 53507)	-
• Temperature °C	-30/+70
• Change of volume	
○ Oil ASTM nr 5 (72H/70°C)	-

Ringmats

○ Oil IRM 903 (72H/70°C)	-
• After ageing	
○ Hardness °Shore A (72H/70°)	-
○ Tensile strength (72H/70°C)	-
○ Elongation (72H/70°C)	-
• Resistance to	
○ Ozone	-
○ Diluted acids	-
○ Concentrated acids	-
○ Aromatic oil	Not
○ Solvents	-

Product versions

Colour	Thickness/ mm	Width / m	Length / m	Execution
Terracotta	23	1.20	0.8	Open base